

Appln. No. 10/706,645

Amendment dated September 18, 2006

Reply to Office Action of May 18, 2006

### Amendments to the Claims

This listing of claims will replace all prior versions, and listings, of claims in the application:

#### Listing of Claims:

1. (Currently amended) A high temperature stable catalyst support comprising the following crystalline structures:

an alumina phase selected from the group consisting of alpha-alumina, theta-alumina and combinations thereof; and

a rare earth aluminate of a hexaaluminate or hexaaluminate-like structure comprising at least one rare earth rare earth metal and having a high molar ratio of aluminum to rare earth metal between 11:1 and 14:1; and

a rare earth aluminate of a perovskite or perovskite-like structure comprising the at least one rare earth metal and having a low molar ratio of aluminum to rare-earth metal of less than 2:1,

~~wherein the rare earth aluminate has with a high molar ratio of aluminum to rare earth metal greater than 5:1, and~~

wherein the catalyst support contains not more than 20% of alpha-alumina, and less than 100 wt% to about 1 wt% of the rare earth aluminate with the high molar ratio of aluminum to rare earth metal.

2. (Currently amended) The catalyst support of claim 1 wherein the catalyst support comprises between 5 and 50 percent by weight of the rare earth aluminate with the high molar ratio of aluminum to rare earth metal based on the total weight of the catalyst support.

3. (Currently amended) The catalyst support of claim 1 wherein the at least one rare earth metal is selected from the group consisting of lanthanum, neodymium, praseodymium, cerium, samarium, and combinations thereof.

4. (Currently amended) The catalyst support of claim 1 wherein ~~the both~~ rare earth aluminates ~~comprises comprise~~ lanthanum.

Appln. No. **10/706,645**  
 Amendment dated September 18, 2006  
 Reply to Office Action of May 18, 2006

5. (Currently amended) The catalyst support of claim 1 wherein the catalyst support comprises between about 1 wt% and about 10 wt% of lanthanum as the at least one rare earth metal.
6. (Currently amended) The catalyst support of claim 1 wherein the rare earth aluminate with the high molar ratio of aluminum to rare earth metal further comprises an element from Groups 1-14 of the Periodic Table of Elements.
7. (Currently amended) The catalyst support of claim 1 wherein the rare earth aluminate with the high molar ratio of aluminum to rare earth metal further comprises nickel, magnesium, barium, potassium, sodium, manganese, a second rare earth metal and or combinations thereof.
8. (Currently amended) The catalyst support of claim 1 wherein the rare earth aluminate with the high molar ratio of aluminum to rare earth metal and the alumina phase are intimately mixed.
9. (Currently amended) The catalyst support of claim 1 wherein the rare earth aluminate with the high molar ratio of aluminum to rare earth metal at least partially coats the alumina phase partially or completely.
10. (Canceled)
11. (Currently amended) The catalyst support of claim 1 wherein the rare earth aluminate with the high molar ratio of aluminum to rare earth metal has a chemical formula of  $\text{LnAl}_y\text{O}_z$ , where y is between 11 and 14; and z is between 18 and 23, Al and O represent aluminum atoms and oxygen atoms respectively; and where Ln comprises lanthanum, neodymium, praseodymium, samarium, ~~cerium~~, or combinations thereof.
12. (Currently amended) The catalyst support of claim 1 wherein the rare earth aluminate with the high molar ratio of aluminum to rare-earth metal has a chemical formula of  $\text{MAl}_y\text{O}_z$ , where y is between 11 and 12; z is between 18 and 19; Al and O represent aluminum atoms and oxygen atoms respectively; and M comprises a combination of lanthanum and samarium.
13. (Currently amended) The catalyst support of claim 1 wherein the rare earth aluminate with the high molar ratio of aluminum to rare-earth metal comprises a lanthanum hexaaluminate.

Appln. No. **10/706,645**

Amendment dated September 18, 2006

Reply to Office Action of May 18, 2006

14-15. (Canceled)

16. (Currently amended) The catalyst support of claim 1 further comprising an oxide of ~~said the~~ at least one rare earth metal.

17. (Original) The catalyst support of claim 1 wherein the catalyst support has a surface area greater than 2 m<sup>2</sup>/gram.

18. (Original) The catalyst support of claim 1 wherein the catalyst support has a surface area lower than 30 m<sup>2</sup>/gram.

19. (Currently amended) The catalyst support of claim 1 wherein the catalyst support comprises between 1 wt% and 10 wt% of the at least one rare earth metal.

20. (Currently amended) The catalyst support of claim 1 wherein the catalyst support is made by impregnating a solution of ~~[[a]]~~ the at least one rare earth metal onto an aluminum-containing precursor; and calcining at a temperature ~~greater than~~ between 1,000° C and 1,600° C.

21. (Original) The catalyst support of claim 20 wherein the aluminum-containing precursor comprises an aluminum structure selected from the group consisting of bayerite, gibbsite, boehmite, pseudo-boehmite, bauxite, gamma-alumina, delta-alumina, chi-alumina, rho-alumina, kappa-alumina, eta-alumina, theta-alumina, and combinations thereof.

22. (Original) The catalyst support of claim 20 wherein the aluminum-containing precursor comprises at least one transition alumina selected from the group consisting of gamma-alumina, delta-alumina, chi-alumina, rho-alumina, kappa-alumina, eta-alumina, and theta-alumina.

23. (Currently amended) The catalyst support of claim 20 wherein the aluminum-containing precursor comprises ~~mostly~~ gamma-alumina.

24. (Currently amended) The catalyst support of claim 23 wherein calcining is done at a temperature between ~~1,000° C~~ about 1,200° C and ~~1,600° C~~ about 1,300° C.

25. (Original) The catalyst support of claim 23 wherein calcining is done at a temperature

Appln. No. 10/706,645

Amendment dated September 18, 2006

Reply to Office Action of May 18, 2006

between 1,100°C and 1,400°C.

26. (Withdrawn) A method for making a thermally stable aluminum-based catalyst support comprising:

- (a) impregnating a solution of a rare earth metal onto an aluminum-containing precursor;
- (b) drying the impregnated aluminum-containing precursor; and
- (c) calcining at a temperature between 1,000 °C and 1,600 °C in a manner effective to convert a portion of said aluminum-containing precursor to an aluminum oxide phase comprising alpha-alumina, theta-alumina, or combinations thereof, and to convert another portion of said aluminum-containing precursor with at least a fraction of said rare earth metal to a rare earth aluminate of a hexaaluminate or hexaaluminate-like structure with a high molar ratio of aluminum to rare-earth rare earth metal greater than 5 between 11:1 and 14:1, and further to a second rare earth aluminate of a perovskite or perovskite-like structure with a low molar ratio of aluminum to rare earth metal of less than 2:1,

such that the catalyst support comprises said rare earth aluminate with the low molar ratio of aluminum to rare-earth metal; the aluminum oxide phase comprising less than 20 wt% of alpha-alumina; and less than 100 wt% to about 1 wt% of said rare earth aluminate with the high molar ratio of aluminum to rare earth metal.

27. (Withdrawn) The method of claim 26 wherein the aluminum-containing precursor comprises an aluminum structure selected from the group consisting of bayerite, gibbsite, boehmite, pseudo-boehmite, bauxite, gamma-alumina, delta-alumina, chi-alumina, rho-alumina, kappa-alumina, eta-alumina, theta-alumina, and combinations thereof.

28. (Withdrawn) The method of claim 26 wherein the aluminum-containing precursor comprises a transition alumina selected from the group consisting of gamma-alumina, delta-alumina, chi-alumina, rho-alumina, kappa-alumina, eta-alumina, theta-alumina, and combinations thereof.

29. (Withdrawn) The method of claim 26 wherein the aluminum-containing precursor

Appln. No. 10/706,645  
 Amendment dated September 18, 2006  
 Reply to Office Action of May 18, 2006

comprises ~~mostly~~ gamma-alumina.

30. (Withdrawn) The method of claim 29 wherein calcining is done at a temperature between 1,000 °C and 1,600 °C about 1,200 °C and about 1,300 °C.
31. (Withdrawn) The method of claim 29 wherein calcining is done at a temperature between 1,100 °C and 1,400 °C.
32. (Withdrawn) The method of claim 26 wherein the rare earth metal is selected from the group consisting of lanthanum, neodymium, praseodymium, cerium and combinations thereof.
33. (Withdrawn) The method of claim 26 wherein the both rare earth aluminates ~~comprises~~ comprise lanthanum.
34. (Withdrawn) The method of claim 26 wherein calcining is further effective to further convert another portion of the rare earth metal solution into an oxide of said rare earth metal, said rare earth oxide consisting essentially of rare earth metal atoms and oxygen atoms.
35. (Withdrawn) The method of claim 26 wherein the solution of rare earth metal comprises more than one rare earth metal.
36. (Canceled)
37. (Withdrawn) The method of claim 26 wherein the rare earth aluminate with the high molar ratio of aluminum to rare earth metal comprises a lanthanum hexaaluminate.
38. (Withdrawn) The method of claim 26 wherein the catalyst support comprises between about 0.5 and about 10 percent by weight of the rare earth metal based on the total weight of the catalyst support.
39. (Withdrawn) The method of claim 26 wherein the catalyst support comprises between about 5 and about 50 percent by weight of the rare earth aluminate with the high molar ratio of aluminum to rare earth metal based on the total weight of the catalyst support.

Appln. No. **10/706,645**

Amendment dated September 18, 2006

Reply to Office Action of May 18, 2006

40. (Currently amended) A partial oxidation catalyst comprising:

(a) an active ingredient comprising a rhodium alloy or a metal selected from the group consisting of rhodium, iridium, ~~platinum, palladium, and ruthenium~~ and combinations thereof, said rhodium being in an amount of from about 0.1 wt% to about 20 wt% based on the total catalyst weight; and

(b) a support onto which the active ingredient is dispersed, said support comprising an alumina phase selected from the group consisting of alpha-alumina, theta-alumina and combinations thereof; and

a rare earth aluminate of a hexaaluminate or hexaaluminate-like structure comprising a rare earth metal, wherein the rare earth aluminate has a and having a high molar ratio of aluminum to rare earth rare earth metal greater than 5 between 11:1 and 14:1; and

a rare earth aluminate of a perovskite or perovskite-like structure comprising the rare earth metal and having a low molar ratio of aluminum to rare earth metal of less than 2:1;

wherein the support comprises less than 100 wt% to about 1 wt% of said rare earth aluminate with the high molar ratio of aluminum to rare earth metal by weight of based on the total weight of the support.

41. (Canceled)

42. (Currently amended) The partial oxidation catalyst of claim 40 wherein the rare earth aluminate with the high molar ratio of aluminum to rare earth metal comprises a lanthanide hexaaluminate, and the lanthanide metal is selected from the group consisting of lanthanum, neodymium, praseodymium, samarium, and combinations thereof.

43. (Original) The partial oxidation catalyst of claim 42 wherein the lanthanide hexaaluminate comprises a lanthanide metal selected from the group consisting of lanthanum, neodymium, praseodymium, and combinations thereof.

44. (Original) The partial oxidation catalyst of claim 42 wherein the lanthanide hexaaluminate comprises lanthanum.

Appln. No. 10/706,645  
 Amendment dated September 18, 2006  
 Reply to Office Action of May 18, 2006

45. (Original) The partial oxidation catalyst of claim 40 wherein the rare earth metal is selected from the group consisting of lanthanum, neodymium, praseodymium, and combinations thereof.
46. (Currently amended) The partial oxidation catalyst of claim 40 wherein ~~the both~~ rare earth aluminates ~~comprises~~ comprise lanthanum.
47. (Currently amended) The partial oxidation catalyst of claim 40 wherein the rare earth aluminate with the high molar ratio of aluminum to rare earth metal comprises more than one rare-earth metal.
48. (Original) The partial oxidation catalyst of claim 40 wherein the support has a surface area greater than 2 m<sup>2</sup>/gram.
49. (Currently amended) The partial oxidation catalyst of claim 40 wherein the support comprises between about 5 and about 50 percent by weight of the rare earth aluminate with the high molar ratio of aluminum to rare-earth metal based on the total weight of the support.
50. (Withdrawn) A method for making synthesis gas comprising:  
 converting a gaseous hydrocarbon stream and an oxygen-containing stream over a partial oxidation catalyst, to make a product stream comprising CO and H<sub>2</sub>,  
 wherein said partial oxidation catalyst includes  
     an active ingredient comprising a rhodium alloy or a metal selected from the group consisting of rhodium, iridium, platinum, palladium, ruthenium, and combinations thereof, said rhodium being in an amount of from about 0.1 wt% to about 20 wt% based on the total catalyst weight; and  
     a support comprising a rare earth aluminate, said rare earth aluminate having a molar ratio of aluminum to rare earth metal greater than 5:1,  
     a support onto which the active ingredient is dispersed, said support comprising  
         an alumina phase selected from the group consisting of alpha-alumina, theta-alumina and combinations thereof;  
         a rare earth aluminate of a hexaaluminate or hexaaluminate-like structure comprising a rare earth metal and having a high molar ratio of aluminum to rare

Appln. No. 10/706,645

Amendment dated September 18, 2006

Reply to Office Action of May 18, 2006

earth metal between 11:1 and 14:1; and

a rare earth aluminate of a perovskite or perovskite-like structure comprising the rare-earth metal and having a low molar ratio of aluminum to rare earth metal of less than 2:1;

wherein the support comprises less than 100 percent to about 1 percent by weight of said rare earth aluminate with the high molar ratio of aluminum to rare earth metal based on the total weight of the support.

51. (Withdrawn) The method of claim 50 wherein the support comprises between about 1 and about 50 percent by weight of said rare earth aluminate with the high molar ratio of aluminum to rare earth metal ~~by weight~~ based on the total weight of the support.

52. (Withdrawn) The method of claim 50 wherein the rare earth metal is selected from the group consisting of lanthanum, neodymium, praseodymium, cerium, and combinations thereof.

53. (Withdrawn) The method of claim 50 wherein the rare earth aluminate with the high molar ratio of aluminum to rare earth metal comprises lanthanum.

54. (Withdrawn) The method of claim 50 wherein the support comprises between about 1 and about 10 percent by weight of lanthanum based on the total weight of catalyst support.

55. (Withdrawn) The method of claim 50 wherein the rare earth aluminate with the high molar ratio of aluminum to rare earth metal comprises lanthanum and samarium.

56. (Canceled)

57. (Withdrawn) The method of claim ~~[[56]]~~ 50 wherein the rare earth aluminate with the high molar ratio of aluminum to rare earth metal and the alumina phase are intimately mixed.

58. (Withdrawn) The method of claim ~~[[56]]~~ 50 wherein the rare earth aluminate with the high molar ratio of aluminum to rare earth metal ~~at least partially~~ coats the alumina phase partially or completely.



Appln. No. 10/706,645  
 Amendment dated September 18, 2006  
 Reply to Office Action of May 18, 2006

59. (Canceled)
60. (Withdrawn) The method of claim 50 wherein the rare earth aluminate with the high molar ratio of aluminum to rare earth metal comprises a lanthanum hexaaluminate.
61. (Withdrawn) The method of claim 50 wherein the support comprises between about 1 wt% and about 10 wt% of the rare earth metal.
62. (Withdrawn) The method of claim 50 wherein the conversion is done at a GHSV between about 20,000 hr<sup>-1</sup> to about 100,000,000 hr<sup>-1</sup>.
63. (Withdrawn) The method of claim 50 wherein the conversion is done at a temperature between about 350 °C to about 2,000 °C.
64. (Withdrawn) The method of claim 50 wherein the conversion is done at a pressure between about 100 kPa to about 4,000 kPa.
65. (Withdrawn) The method of claim 50 wherein the hydrocarbon stream comprises natural gas.
66. (Withdrawn) The method of claim 50 wherein the hydrocarbon stream comprises mainly at least about 50% by volume of methane.
67. (Withdrawn) The method of claim 50 wherein the partial oxidation catalyst comprises rhodium.
68. (Withdrawn) The method of claim 67 wherein the partial oxidation catalyst comprises between about 0.5 wt% and about 10 wt% of rhodium.
69. (Withdrawn) The method of claim 67 wherein the partial oxidation catalyst has a rhodium surface area greater than about 0.5 m<sup>2</sup>/g.
70. (Withdrawn) The method of claim 67 wherein the partial oxidation catalyst further comprises samarium.

Appln. No. **10/706,645**

Amendment dated September 18, 2006

Reply to Office Action of May 18, 2006

71. (Withdrawn) The method of claim 50 wherein the catalyst exhibits hydrocarbon conversion of equal to or greater than about 85%.
72. (Withdrawn) The method of claim 50 wherein the partial oxidation catalyst has a hydrogen selectivity equal to or greater than about 85%.
73. (Withdrawn) The method of claim 50 wherein the product stream comprising CO and H<sub>2</sub> has a H<sub>2</sub>:CO molar ratio between about 1:4:1 and 2.3.
74. (Withdrawn) The method of claim 50 wherein at least a portion of the product stream comprising CO and H<sub>2</sub> is further converted to hydrocarbons.
75. (Canceled)
76. (Currently amended) The catalyst support of claim 1 wherein the catalyst support comprises between 1 and 50 percent by weight of the rare earth aluminate with the high molar ratio of aluminum to rare earth metal based on the total weight of the catalyst support.
77. (Currently amended) The catalyst support of claim 1 wherein the catalyst support comprises more than 40 wt% ~~of rare earth aluminate~~ and less than 100 wt% of the rare earth aluminate with the high molar ratio of aluminum to rare earth metal based on the total weight of the catalyst support.
78. (Withdrawn) The method of claim 26 wherein the catalyst support comprises between about 1 and about 50 percent by weight of the rare earth aluminate with the high molar ratio of aluminum to rare earth metal based on the total weight of the catalyst support.
79. (Withdrawn) The method of claim 26 wherein the catalyst support comprises more than 40 wt% ~~of rare earth aluminate~~ and less than 100 wt% of the rare earth aluminate with the high molar ratio of aluminum to rare earth metal
80. (Currently amended) The partial oxidation catalyst of claim 40 wherein the support comprises between about 1 and about 50 percent by weight of the rare earth aluminate with the

Appln. No. 10/706,645

Amendment dated September 18, 2006

Reply to Office Action of May 18, 2006

high molar ratio of aluminum to rare earth metal based on the total weight of the support.

81. (Currently amended) The partial oxidation catalyst of claim 40 wherein the support comprises more than 40 wt% of ~~rare earth aluminate~~ and less than 100 wt% of the rare earth aluminate with the high molar ratio of aluminum to rare earth metal based on the total weight of the support.

82. (Canceled)

83. (New) The catalyst support of claim 40 wherein the support comprises not more than about 20 wt% alpha-alumina.

84. (New) The catalyst of claim 40 wherein the partial oxidation catalyst comprises a rhodium alloy, said rhodium alloy comprising a metal selected from the group consisting of ruthenium, iridium, platinum, palladium, tantalum, niobium, molybdenum, rhenium, tungsten, cobalt, and zirconium.

85. (New) The catalyst of claim 40 wherein the partial oxidation catalyst comprises between about 0.5 wt% and about 10 wt% of rhodium.

86. (New) A partial oxidation catalyst comprising:

(a) an active ingredient comprising rhodium or a rhodium alloy, said rhodium alloy comprising rhodium and a metal selected from the group consisting of ruthenium, iridium, platinum, palladium, tantalum, niobium, molybdenum, rhenium, tungsten, cobalt, and zirconium, said rhodium being in an amount of from 0.1 wt% to about 20 wt% based on the total catalyst weight; and

(b) a support onto which the active ingredient is dispersed, said support comprising:  
an alpha-alumina phase;

less than 100 percent to about 1 percent by weight of a rare earth aluminate of a hexaaluminate or hexaaluminate-like structure, with a high molar ratio of aluminum to rare-earth metal between 11:1 and 14:1, and comprising at least one rare earth metal selected from the group

Appln. No. 10/706,645

Amendment dated September 18, 2006

Reply to Office Action of May 18, 2006

consisting of lanthanum, neodymium, praseodymium, samarium, and combinations thereof; and  
a rare earth aluminate of a perovskite structure comprising the at least one rare earth metal  
with a low molar ratio of aluminum to rare-earth metal of less than 2:1.

87. (New) The partial oxidation catalyst of claim 86 wherein the rare earth aluminate with the high molar ratio of aluminum to rare-earth metal comprises between 5 and 45 percent by weight of the total weight of the catalyst support.

88. (New) The partial oxidation catalyst of claim 86 wherein the rare earth aluminate with the high molar ratio of aluminum to rare-earth metal comprises more than 40 percent and less than 100 percent by weight of the total weight of the catalyst support.

89. (New) The partial oxidation catalyst of claim 86 wherein the partial oxidation catalyst comprises between about 0.5 wt% and about 10 wt% of rhodium.

90. (New) The partial oxidation catalyst of claim 86 wherein the partial oxidation catalyst comprises rhodium and has a rhodium surface area greater than about 0.5 m<sup>2</sup>/g rhodium.